



Lliça Packagin Slu
Carretera Sabadell a
Granollers Km 11,1
08185 Lliça de Vall (Spain)

TEL :
France +33 (0) 1 46 35 12 37
(Cadex)
Spain: +34 934 759 100
(Careo Iberica)
email: info@llissapackaging.com

Lliça Kraft

Multilayer kraft back board

Carton blanchie avec verso non blanchie (kraft)

Specification	unit	Tolerances	175	220	235	255	290	315	350	380
Caliper / Epaisseur	µm	± 5%	260	370	405	445	500	567	632	688
Stiffness/ Rigidité (Taber-CD)	mN.m	± 15%	2,1	5,7	7,3	9,6	12,8	16,2	20,4	24,5
Stiffness (Taber- MD)	mN.m	± 15%	4,4	12,0	15,3	20,2	29,5	37,4	46,9	56,4

Substance / Grammage	g/m2	+3%/-5%	ISO							
Burst strenght	Kpa	630	ISO							
Brightness / Blancheur	C/2, %	min 78	80.0							
Moisture	%	± 1	7.0	7.0	7.5	7.5	8.0	8.5	9.0	9.5
COBB 60	g/m2	Top/Back	30.0							
Scott bond	J/m 2	min 100	175	175	200	200	200	180	180	180
Edge wicking	g/mm.m	max 1.0	0.5	0.5	0.5	0.5	0.5	0.5	0.5	0.5
SCT MD	kN/m	4.0								
Robinson test			<1 for on year stored under normal conditions							